



Government of the Peoples Republic of Bangladesh  
Quality Control & Training Division, BRRL



DATA & REPORT SHEET

Memo No: LAB-26-06-22-03920-001-01

Date: 2026-06-22

Client : Narayanganj Road Division Lab Register No. : 105 (B) 2025-2026.  
Tender No. : 1272667 Contract No. : Nill  
Tracking Number : LAB-26-06-22-03920 Sample Sent By : Client  
Project/Work Name : Repair of Flexible Pavement & HBB Work at 4th (p) of Anandabazar-Barudi-Taltola Road (Z-1067) under Narayanganj Road Division during the year 2025-2026. Tender Package No. Nill. (Tender ID: ).  
Sample Collection From : From Stackyard Sample Source : Nill  
Sample Sealing Status : Sealed Sample Collected By : EE (RHD)  
Name of Test : BITUMEN ROUTINE TEST  
Item Name : Others Test Code : BRRL  
Test Method : ASTM  
Associated Agency : Anowara Corporation. Address: Delpara, Kutubpur, Fatullah, Narayanganj-1421.  
Date of sample receive : 18/06/2026 Date of Test : 21/06/2026  
at Lab  
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 3 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division Narayanganj.  
Test Performed By : Akram Hossen Test Supervised By : Sheikh Nafiur Nur Mousum  
Assistant Research Officer

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	65		ASTM D-5	60 - 70	80/100
Softening Point	°C	48		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.08		ASTM D-6	≤ 0.2	≤ 0.5
Penetration of residue from loss on heating test at 25°C, 100g, 5 Sec, as compared to penetration before heating	%	83.08		ASTM D-5&6	≥ 80	≥ 80
Flash point	°C	305		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.375				
Weight of Pycnometer +Water, B	gm	56.138				
Weight Pycnometer partially filled with Bitumen, C	gm	44.830				
Pycnometer+Bitmen+Water, D	gm	56.427				
Density of Water at 25 °C, G25	Kg/m <sup>3</sup>	1000				
Temperature of Water (T); °C,	°C	25				
Density of Water at Temperature T °C( GT )	Kg/m <sup>3</sup>	1000				
SP. Gravity= $\frac{(C-A)}{(B-A)-(D-C)} \times (GT/G25)$		1.0204				
Specific Gravity		1.0204				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

22-Jun-2026

Akram Hossen

Test Approved By

22-Jun-2026

Sheikh Nafiur Nur Mousum

Counter Signed By

22-Jun-2026

Sheikh Nafiur Nur Mousum

Counter Signed By

22-Jun-2026

Dewan Abul Kashem  
Mohammad Nahin Reza  
Executive Engineer  
Quality Control & Training  
Division, BRRL

Assistant Research Officer(AC)  
Quality Control & Training  
Division, BRRL

Assistant Engineer  
Quality Control & Training  
Division, BRRL

Sub Divisional Engineer(AC)  
Quality Control & Training  
Division, BRRL

This is a auto generated report by OLTMS system.